

WMC Sinterstar AG
Bahnstrasse 1
CH-4932 Lotzwil
Tel. +41 (0)62 919 70 40 Fax +41 (0)62 919 70 50

info@wmc-sinterstar.ch

Sorte Grade	UM30 HIP	ISO-Bereich ISO-Range	K30UF
----------------	-----------------	--------------------------	-------

Chemische Zusammensetzung Chemical composition			Physikalische Daten Physical information		
WC	90.0	wt%	Mittlere WC Korngrösse Average grain size		Ultrafein/ Ultrafine (0.5 µm)
TiC		wt%	Dichte Density		14.50 g/cm ³
Ta/NbC	0.5	wt%	Härte Hardness		1770 HV30
Co	9.0	wt%	Risszähigkeit Fracture strength		8.7 N/mm ² ·m ^(1/2)
Ni		wt%	Biegebruchfestigkeit Transverse rupture strength		3800 N/mm ²
Andere Other	0.5	wt%	Druckfestigkeit Compressive strength		6000 N/mm ²
Porosität / Porosity	A02 <B02 C02 Eta 00		E-modul Young's module		600 kN/mm ²
			Wärmeleitfähigkeit Thermal conductivity		81 W/mK
			Wärmeausdehnungskoeffizient Thermal expansion coefficient		5.5 10 ⁻⁶ K

Bemerkungen / Comments:

Typische Gefügestruktur / Grade structure

